

Material Type: Manganese-Zinc Ferrite

Properties: Very high permeability
High curie temperature
High saturation flux density

Frequency Range: DC to 300 kHz (subject to application)

Typical Application: Broadband and pulse transformers, common mode chokes and inductors


Standard Geometries: Toroids, baluns, EP and pot cores
Additional shapes are available upon request




Parameter	Symbol	Standard Test Conditions			Unit	Value
Initial Permeability <i>(nominal)</i>	μ_i	B < 0.1 mT	f = 10 kHz	T = 25°C	-	7500
Saturation Flux Density <i>(typical)</i>	B_s	H = 796 A/m (10 Oe)		T = 25°C	mT	420
Remanent Flux Density <i>(typical)</i>	B_r	H ~ 0 A/m (from near saturation) f = 10 kHz		T = 25°C	mT	130
Coercivity <i>(typical)</i>	H_c	B ~ 0 mT (from near saturation) f = 10 kHz		T = 25°C	A/m	10
Loss Factor <i>(maximum)</i>	$\frac{\tan \delta}{\mu_i}$	B < 0.1 mT	f = 100 kHz	T = 25°C	10 ⁻⁶	50
Curie Temperature <i>(minimum)</i>	T_c	B < 0.1 mT	f = 10 kHz		°C	150
Resistivity <i>(typical)</i>	ρ	E = 1 V/cm		T = 25°C	$\Omega \cdot \text{cm}$	10

* Data was derived from measurements made on a standard test toroid core with an outside diameter of 30 mm


Dynamic Magnetisation Curve



Permeability vs Temperature



Loss Factor vs Frequency



Permeability vs Frequency

