


Material Type:	Manganese-Zinc Ferrite
Properties:	Very high permeability High curie temperature High saturation flux density
Frequency Range:	DC to 300 kHz (subject to application)
Typical Application:	Broadband and pulse transformers, balanced and common mode chokes, T1/E1 and DSL transformers
Standard Geometries:	Toroids, baluns, EP and pot cores Additional shapes are available upon request




Parameter	Symbol	Standard Test Conditions			Unit	Value
Initial Permeability (nominal)	μ_i	$B < 0.1 \text{ mT}$	$f = 10 \text{ kHz}$	$T = 25^\circ\text{C}$	-	10000
Saturation Flux Density (typical)	B_s	$H = 796 \text{ A/m (10 Oe)}$		$T = 25^\circ\text{C}$	mT	420
Remanent Flux Density (typical)	B_r	$H \sim 0 \text{ A/m (from near saturation)}$ $f = 10 \text{ kHz}$		$T = 25^\circ\text{C}$	mT	180
Coercivity (typical)	H_c	$B \sim 0 \text{ mT (from near saturation)}$ $f = 10 \text{ kHz}$		$T = 25^\circ\text{C}$	A/m	8
Loss Factor (maximum)	$\frac{\tan \delta}{\mu_i}$	$B < 0.1 \text{ mT}$	$f = 100 \text{ kHz}$	$T = 25^\circ\text{C}$	10^{-6}	50
Curie Temperature (minimum)	T_c	$B < 0.1 \text{ mT}$	$f = 10 \text{ kHz}$		$^\circ\text{C}$	150
Resistivity (typical)	ρ	$E = 1 \text{ V/cm}$		$T = 25^\circ\text{C}$	$\Omega \cdot \text{cm}$	10

* Data was derived from measurements made on a standard test toroid core with an outside diameter of 30 mm


Dynamic Magnetisation Curve



Permeability vs Temperature



Loss Factor vs Frequency



Permeability vs Frequency

